

## Technical Instruction Sheet

page 1 of 2

**Characteristics:**

AKEPOX® 2020 is a viscous, solvent-free 2-component adhesive based on an epoxy resin containing fillers and a modified polyamine hardener. The product is distinguished by the following qualities:

- extremely low shrinkage during the hardening process and therefore low tensions in the bonding layer
- extremely weather resistant bondings
- a good thermal stability: approx. 60-70°C for bonded parts exposed to weight, approx. 100-110°C for bonded parts not exposed to weight
- a good dimensional stability of the bonding layer
- a small tendency to fatigue
- a very good alkali-stability, thus the adhesive is very well suited to bond concrete.
- excellently suited for bonding gas-impermeable materials as it is a solvent-free product
- suited for bonding load-bearing construction parts
- good electrical insulating property
- good adhesion on slightly humid stones
- suited for bonding materials which are sensitive to solvents (e.g. expanded polystyrene, ABS)
- the product is not liable to crystallise, therefore no problems in storing and processing.

**Field of Application:**

AKEPOX® 2020 is mainly used in the stone processing industry for bonding of natural stones (marble, granite), cast stones or building material (concrete, terrazzo) and steel. Due to a certain stability conditioned by its structure the product can be applied as well vertically up to a layer thickness of about 2 mm; even extremely uneven surfaces can be bonded. In horizontal areas grooves and bore-holes for instance, which hold metal (steel) reinforcements or metal hooks can be filled. Other materials s. a. plastics (rigid PVC, polyester, polystyrene, ABS, polycarbonate), paper, wood and glass can be bonded. Metal parts coated with AKEPOX® 2020 are very well protected against corrosion. Materials e.g.. polyolefin (polyethylene, polypropylene), silicone, fluorohydrocarbons (Teflon), flexible PVC and butyl rubber can not be bonded with AKEPOX® 2020.

**Instructions for Use:**

1. Thoroughly clean and slightly roughen surfaces to be bonded.
2. Thoroughly mix 2 parts (volume or weight) of component A with 1 part (volume or weight) of component B until a homogeneous shade of colour is achieved.
3. AKEPOX® Colouring Pastes can be added up to max. 5 %.
4. The mixture remains workable for approx. 40-50 min (20°C). After 6-8 hrs (20°C) the bonded parts may be moved, after 12-16 hrs (20°C) approx. they may be further processed. Max stability after 7 days (20°C).
5. Tools can be cleaned with AKEMI Nitro-Dilution.
6. The hardening process is accelerated by heat and delayed by cold.
7. If stored in cool place, approx. shelf life is 1 year.

**Special Hints:**

- Metallic surfaces should be ground in a short interval before bonding to avoid a decrease in adhesion.
- Only if the right mixing ratio is kept, optimal mechanical and chemical properties can be obtained. A surplus of adhesive or hardener has the effect of a softener.
- Use AKEMI Liquid Glove to protect your hands.
- Two separate spatulas should be used for the hardener and the adhesive.
- An adhesive which is already thickened or just gelling should not be used anymore.
- At temperatures below 10°C the product should not be used anymore as there is no sufficient hardening.

## Technical Instruction Sheet

- The hardened adhesive is liable to yellowing when exposed to sunlight and is therefore not suited for fillings or visibly bonded joints on light-coloured or white surfaces.
- Once hardened, the adhesive can no longer be removed by solvents. Removal is only possible mechanically or by higher temperatures (> 200°C).
- When worked correctly, the hardened adhesive is not damaging to health.

**Safety Measures:**

see EC Safety Data Sheet

**Technical Data:**

1. Component A	Colour:	light beige-grey
	Density:	approx. 1.53 g/cm <sup>3</sup>
Component B	Colour:	khaki-grey
	Density:	approx. 1.50 g/cm <sup>3</sup>

## 2. Working Time

a) mixture of 100 g of component A + 50 g of component B

at 10°C:	110 - 120 minutes
at 20°C:	40 - 50 minutes
at 30°C:	20 - 30 minutes
at 40°C:	10 - 20 minutes

b) at 20°C and different quantities

20 g of component A + 10 g of component B:	60 - 70 min
50 g of component A + 25 g of component B:	50 - 60 min
100 g of component A + 50 g of component B:	40 - 50 min
300 g of component A + 150 g of component B:	35 - 45 min

## 3. Hardening process (shore-D-hardness) of a 2 mm layer at 20°C

<u>3 hrs</u>	<u>4 hrs</u>	<u>5 hrs</u>	<u>6 hrs</u>	<u>7 hrs</u>	<u>8 hrs</u>	<u>24 hrs</u>
--	33	35	54	65	72	80

## 4. Mechanical Properties

Bending strength DIN 53452:	50 - 60 N/mm <sup>2</sup>
Tensile strength DIN 53455:	20 - 30 N/mm <sup>2</sup>
E-module:	5500 - 6000 N/mm <sup>2</sup>

## 5. Chemical Resistance

Water absorption DIN 53495	> 0.5 %
Sodium Chloride Solution 10%	stable
Salt Water	stable
Ammonium 10%	stable
Soda Lye 10%	stable
Hydrochloric acid 10%	stable
Acetic acid 10%	conditionally stable
Formic acid 10%	conditionally stable
Petrol	stable
Diesel oil	stable
Lubricating oil	stable

6. Shelf life: 1 year approx. if stored in cool place free from frost in its tightly closed original container.

**Notice:**

The above information is based on the latest stage of technical progress. It is to be considered as a non-binding hint and does not release the user from a performance test, since application, processing and environmental influences are beyond our realm of control.