

Specification sheet

page 1 of 4

Properties:

AKEMI® BF 200 UP Injection mortar is a two-component reactive resin mortar on the basis of unsaturated polyester resins dissolved in styrene. The product is characterized by the following properties:

- certified for masonry in accordance with DIN 1053 by the building supervisory authority (No. Z-21.3-1821)
- safe and reliable processing and application due to the cartridge system
- suitable for natural stone, masonry and concrete
- uniform load transmission on account of a non-splaying anchorage system
- also suitable for anchoring close to edges
- excellent interconnection and tight fit between the injection mortar, mesh sleeve, anchor (tie) rod and the surrounding embedment material
- good surface drying
- bonded parts are impermeable to water and have a reliable long-term behaviour
- long-term heat resistance to 50 °C, short-term resistance to 80 °C
- simple dosage and mixing on account of the cartridge system

Application areas:

AKEMI® Anchoring system BF 200 UP is mainly used in order to anchor galvanised or stainless steel anchor rods, threaded sleeves, reinforcing bars, profiled sections or the like for the following purposes:

- heavy-duty fixing to solid stone, concrete and
- medium-load fixing to vertically perforated brick ≥ HLz 4 in accordance with DIN 105, perforated sand-lime brick ≥ KSL 4 in accordance with DIN 106, hollow blocks made of light-weight concrete ≥ Hbl 2 in accordance with DIN 18151 and hollow blocks made of concrete ≥ Hbn4 in accordance with DIN

for facades, canopies/porches, wooden and metal constructions, metal profile sections, brackets, balustrades, gratings, heating and sanitary installations, piping, cable runways, high racks, lighting etc.

Instructions for use:

- 1. Drill the hole (rotary or impact drilling) without cooling liquid in accordance with the characteristic value table; in the case of light-weight or aerated concrete, drill a tapered hole.
- 2. Clean the drill hole (solid brick: blow out once, brush out once, blow out again, brush out again, blow out again; perforated brick: blow out once, brush out once, blow out again)
- 3. In the case of masonry, insert a mesh sleeve.
- 4. Working temperature of the cartridge +20 °C, object temperature +5 to +35 °C.
- 5. Insert the cartridge into the gun, screw on the mixer and discard approx. 10 cm of the mortar; please pay attention to the working times in the reaction
- 6. Insert the mixer to the bottom of the drill hole and fill from bottom to top with the reaction mortar. If using a mesh sleeve, use the mixer attachment to fill.
- 7. Insert the threaded rod or the reinforcing iron bar to the marking by turning it with the hand, check the filling level.
- 8. Refer to the reaction table for the hardening times.
- 9. Attach the component and apply the torque in accordance with the characteristic value table.

Concrete or solid brick







see 2.





see 6.







see 5.



Specification sheet

page 2 of 4

Aerated or light-weight concrete

















see 1.

see 2. see 5.

see 7.

see 8.

Masonry in accordance with DIN 1053 (solid and vertically perforated brick, solid sand-lime and perforated sand-lime brick)

















see 1.

see 2.

see 2.

see 3.

see 5.

5.

see 6.

see 7.

see 8.



see 9.

Special remarks:

- if the drill holes are damp or badly cleaned, the strength of the bond will be reduced
- the regulations laid down in the general certification from the building supervisory authority (No. Z-21.3-1821) are to be adhered to (see the certification document)
- use anchor rods made of galvanised steel with DIBT approval for covered areas (indoors) with the exception of rooms with high humidity. Use anchor rods made of stainless steel (1.4401/1.4571) with DIBT approval for rooms with high humidity, in the open air (outdoors), in industrial surroundings and near the sea
- mortar which has already started to jellify, may no longer be used
- at temperatures below +5 °C, hardening will be significantly delayed
- mortar which has already hardened can no longer be removed with solvents. At this stage it can only be removed mechanically or using high temperatures (>200 °C)
- if processed correctly, the fully-hardened product presents no hazard to health
- drill holes may not be made with diamond drills because the surface of the hole would be too smooth, thus considerably reducing mechanical interlocking with the injection mortar

Safety notices:

Please refer to the EC safety data sheet

Technical specifications:

1. Reaction table

Object temperature	Working time	Hardening time
5 °C	20 – 25 min	120 min
10 °C	10 – 15 min	80 min
20 °C	5 – 6 min	45 min
30 °C	3 – 4 min	25 min
35 °C	1 – 2 min	20 min

The temperature of the material in which the anchoring is to take place may not fall below + 5 °C during hardening.



Specification sheet

page 3 of 4

2. Characteristic value table - concrete

Wall plug size/anchor rod		M8	M10	M12	M16	M20	M 24
Depth of embedment of	h _{nom} [mm]	80	90	110	125	170	210
the anchor rod							
Diameter of the anchor	d [mm]	8	10	12	16	200	24
Nominal diameter of drill	d _o [mm]	10	12	14	18	24	28
bit							
Diameter of drill hole	d _{cut} [mm]	10,45	12,45	14,5	18,5	24,55	28,55
Depth of drill hole	h ₀ [mm]	80	90	110	125	170	210
Clearance hole in the	d _f [mm]	9	12	14	18	22	26
component to be attached							
Brush diameter	d _b [mm]	12	14	16	20	27	30
max. torque when	T _{inst} [Nm]	10	20	40	60	150	200
fastening							
Distance to edge	c _{min} [mm]	120	135	165	187,5	255	315
Min. spacing	s _{min} [mm]	120	135	165	187,5	255	315
Min. thickness of	h _{min} [mm]	110	130	160	160	250	300
component							

3. Characteristic value table - masonry

Mesh sleeve	SH 15/85 SH		115/100 ¹⁾		
Wall plug size/anchor rod	M8	M8	M10		
Nominal diameter of drill bit	d _o [mm]	16 16			
Depth of drill hole	t [mm]	90	10	05	
Depth of the mesh sleeve	[mm]	85	10	00	
Depth of embedment of the anchor rod	h _{ef} [mm]	80	80	90	
Centre distance (group of wall plugs) ≥ a [mm]		100			
	min a [mm]	50)		
Min. spacing (single wall plugs)	$= a_z [mm]$	250			
Distance to edge	≥ a _r [mm]	200 (250) ²⁾			
Distance to edge under special conditions ³⁾	≥ a _r [mm]	50 (60) ²⁾			
Min. thickness of component	d [mm]	110			
Max. torque when fastening	T _{inst} [Nm]	2			
Clearance hole in the component to be attached	≤ [mm]	9 12		12	

- 1) For the allocation of the mesh sleeves see section 4
- 2) Value in brackets applies for solid bricks (Mz and KS)
- 3) Applies for masonry with superimposed load or proof of stability. Does not apply if the shear load is directed towards the free edge.

4. Allocation of the mesh sleeves to the embedment materials

Mesh sleeve		Wall plug size	Embedment material
Type	I _s [mm]		
SH 15/85	85	M8	≥ Mz 12, ≥ Hlz 4
SH 15/100	100	M8	≥ KS 12, ≥ KSL 4
		M10	≥ Mz 12, ≥ Hlz 4
			≥ KS 12, ≥ KSL 4



Specification sheet

page 4 of 4

5. Performance data - concrete

Recommended load F_{rec.} [kN] inclusive of safety factor calculated in accordance with ETAG; values valid for anchor rods made of galvanised steel strength category 5.8 or stainless steel 1.4401/1.4571 strength category A4-70

Wall plug size/anchor	r rod	M8	M10	M12	M16	M20
Concrete ≥ C20/25	F _{rec.} [kN]	4.1	6.2	8.9	9.9	11.4
Concrete ≥ C12/15		3.2	4.8	6.9	7.7	8.8
Aerated concrete		1.2	1.2	1.2	-	-

6. Performance data - solid brick

Permissible load F_{perm.} [kN] (tensile, transverse and diagonal tensile load at every angle)

Wall plug size/anchor rod		M8	M10	M12
Solid brick ≥ Mz 12	F _{perm.} [kN]	1.7	1.7	1.7
Solid sand-lime brick ≥ KS	•	1.7	1.7	1.7
12				

7. Performance characteristics - perforated brick

Permissible/recommended load F_{perm,/rec.} [kN] (tensile, transverse and diagonal tensile load at every angle)

Wall plug size/anchor rod		M8	M10	M12
Vertically perforated brick	F _{perm.} [kN] ≥ Hlz 4	0.3	0.3	0.3
	F _{perm.} [kN] ≥ HIz 6	0.4	0.4	0.4
	F _{perm.} [kN] ≥ Hlz 12	0.8	0.8	0.8
Perforated sand-lime brick	F _{perm.} [kN] ≥ KSL 4	0.4	0.4	0.4
	F _{perm.} [kN] ≥ KSL 6	0.6	0.6	0.6
	F _{perm.} [kN] ≥ KSL 12	0.8	0.8	0.8
Hollow block made of light-	F _{rec} [kN] ≥ Hbl 2	0.3	0.3	0.3
weight concrete	F _{rec.} [kN] ≥ Hbl 4	0.6	0.6	0.6
Hollow block made of con-	F _{rec.} [kN] ≥ Hbl 4	0.6	0.6	0.6
crete				

8. Shelf life: Approx. 1 year in the firmly closed original container under cool and frost-free

conditions.

Notice: The above specifications were made on the basis of the present-day stage of

technological development as well as the application research of our company. Because the ways and means of application are beyond our control, the manufacturer cannot be made liable for the contents of this specification

sheet.

Art. No. 5 07 00 TIS 03.07