



PolyVers International
 87 Shawnee Avenue
 Kansas City, KS 66105
 (913) 321-9000
 (913) 321-1490 (fax)

Product Data Sheet

PV 104 Industrial & Chemical Resistant Epoxy

Product Description- *PolyVers PV 104* is an epoxy concrete floor coating that offers an economical and highly serviceable coating for areas subject to harsh chemical exposure. **PV 104** is a self-priming and semi-leveling two part epoxy that can be sprayed or hand applied.

Uses- *PolyVers PV 104* is an excellent industrial epoxy where affordability is a requirement. **PV 104** is designed to offer chemical resistance and protective coating for concrete structures that experience heavy wear and abuse.

Ideal for Applications In-

- Process Slabs
- Tank Farm Floors
- Chemical Loading and Unloading Areas
- Spill Containment Areas
- Waste-Proofing

Advantages-

- Low Permeability
- 100% solid
- Excellent resistance to:
 - Chemical Attack
 - Wear and Impact
 - Thermal Shock
 - Cracking
- High Cohesive Strength and Flexibility

Physical Properties-

Solids by Volume	Volume	100%
Pot Life	24°C (75°F)	45-60 minutes
Cure Time	24°C (75°F)	Foot Traffic: 12 hrs Light Vehicular Traffic: 24 hrs Chemical Service: 36 hrs
Hardness	ASTM D-2240	68-72 Shore D
Compressive Strength	ASTM C-579	12,000 psi
Flexural Strength	ASTM D-790	10,000 psi
Tensile Strength	ASTM D-638	4,500 psi
Elongation	ASTM D-638	8%
Permeability	ASTM E-96	0.006 perm

Application Guidelines-

TEMPERATURE CONSIDERATIONS-

1. Throughout the application process the surface temperature should remain above 10°C (50°F).
2. Store all materials at 21°C (70°F) - 29°C (85°F) for at least 24 hours prior to use.

SURFACE PREPARATION OF CONCRETE-

1. Surface must be free of dirt, dust, oil, grease, chemical and other contaminants immediately prior to applying **PV 104**
2. New concrete should be cured a minimum of 28 days.
3. Concrete must be structurally sound and must not contain any accelerators or curing compounds.
4. Remove all oil and grease.
5. Remove all surface laitance and expose sound concrete. We recommend abrasive blasting to do

- this. However, other methods, such as acid etching and neutralizing, may be used.
6. In general, any existing coating should be completely removed.
 7. Honeycomb and form voids on vertical surfaces may be filled using VersaGrout 100 or 200.

PRIMING- PolyVers PV 104 can act as a self priming coating or in conjunction with a **PolyVers** primer. The use of a primer such as the PV 30, PV 31, PW-1 or PV 20 is recommended. Refer to the data sheet for further application information. When using the **PV 104** as a self priming coating, apply a thin 5-10 mil coating and follow the same procedures and guidelines as described within.

APPLICATION EQUIPMENT- PolyVers PV 104 may be applied using a single component airless sprayer, 4 to 1 plural component proportioner, brush, or roller. Contact **PolyVers** for further equipment recommendation and set up.

MIXING AND APPLICATION

1. The A and B Components should be pre-mixed immediately prior to use.
2. If using a plural component proportioner, follow equipment manufacturer recommendation for equipment operations.
3. If using a single component airless sprayer or roller:
Pour the entire contents of Part B into the container holding Part A and mix thoroughly for two minutes with a jiffy type mixer.
The pot life of the mixture will be approximately 45-60 minutes @ 24°C (75°F); elevated temperatures and extended time in the bucket will shorten the pot life.
4. If self priming apply a 5-10 mil coat.
5. If applying as a coating thickness can be up to 20 mils. For thicker films, additional coats are needed.
6. To prepare the coating for intercoat adhesion:
Allow **PV 104** to cure until gelled.
If the surface cures firm to the touch, but it is less than 24 hours, it **MUST** be washed with soap and water, rinsed, and dried before recoating.
Surface cured beyond 24 hours **MUST** be washed with soap and water, rinsed, dried, and lightly sanded or abrasive blasted.

Packaging-

PV 104 is available in 1 gallon, 5 gallon, and 25 gallon kits. Each kit comes with a premeasured Part A and Part B component. A bagged Part C thixotrope is available for vertical work.

Storage and Shelf Life-

Keep **PV 104** components in their original containers, tightly sealed. When stored at 10°C (50°F) – 24°C (75°F) out of direct sunlight **PV 104** has a shelf life of one year.

Clean Up- PV 104 may be removed from tools and equipment using xylene or MEK.

Safety-

FOR INDUSTRIAL USE ONLY.

Avoid contact with eyes and skin. Do not ingest or inhale

When working with **PV 104** always wear chemical goggles, rubber gloves, and appropriate work clothes.

Prolonged or repeated exposure to **PV 104** may cause skin irritation or allergic reactions.

Refer to the MSDS regarding individual components, additional safety precautions, and proper clean up procedures.

Technical Services-Sales and Customer Support (913) 321-9000

Warranty-PolyVers International will refund the price of or replace, at its election, product it finds to be defective provided the product has been used properly. Except as expressly stated above, the Company makes no warranty of merchantability and no warranty of fitness for any particular purpose, nor does it make any warranty, expressed or implied, of any nature whatsoever with respect to the product or its use. In no event shall the company be liable for delay caused by defects, for loss of use, for indirect, special or consequential damages, or for any charges or expenses of any nature incurred without its written consent.